ISSN 2189-7107



PRINT ISSN 1342-0852 KURRI- KR208

The 7th Japan-Taiwan joint meeting on neutron and X-ray scattering

Proceedings

March 11th ~ 12th, 2016

Edited by the organizing committee of The 7th Japan-Taiwan Joint meeting on neutron and X-ray scattering

Research Reactor Institute, Kyoto University

Preface

It is my honour to hold The 7th Japan-Taiwan joint meeting on neutron and X-ray scattering in Kumatori. The Japan-Taiwan joint meeting on neutron and X-ray scattering has been held bilaterally in Japan and Taiwan. In these meetings, we discuss the synchrotron X-ray and neutron scattering studies on bio-materials, soft-materials and nano-materials, and in addition we also discussed collaboration between Taiwan and Japan based on the synchrotron X-ray facility in Hsinchu, Taiwan and the neutron scattering facilities as well as the synchrotron facilities in Japan. The progress of this meeting is briefly followed. The 1st meeting was held at Tokai, Japan in December, 2006, the 2nd meeting was held at Wulai, Taiwan in December, 2007, the 3rd meeting was held at Kyoto, Japan in December, 2008, the 4th meeting was held at Yilan, Taiwan in March, 2010, the 5th meeting held at Tokai, Japan in February, 2013, the 6th meeting was held at Taipei, Taiwan in March, 2014, and the 7th this meeting is held at Kumatori, Japan in March, 2016.

This meeting will provide the recent outstanding results in the fields of fundamental polymer and biological sciences and their applications as well. In the fields of the X-ray and/or neutron scattering, the methodological progress expands the research fields and gives us new scientific insights. This meeting invites the researchers developing new methodologies, such as dynamics measurement utilizing nuclear Bragg resonance, subunit-kinetics measurement with deuteration-assisted small-angle neutron scattering and so on. I am anticipating that the participants find new methods to apply their research issues. In addition, neutron can be used not only for a probe to investigate a material structure but also for the medical purpose. A special lecture of the recent achievement and future perspective of Boron Neutron Capture Therapy will be provided by Prof. Ono, who is a pioneer of this therapy.

I am expecting that the collaboration between Taiwan and Japan will be enhanced through the scientific discussion and also personal understanding in this meeting.

Sincerely,

Masaaki Sugiyama

Chairman, The 7th Japan-Taiwan joint meeting on neutron and X-ray scattering

PROGRAM March 11th

9:00-9:25	Reception
9:25-9:35	Opening Remarks Yuji Kawabata (Director of Research Reactor Institute, Kyoto University)
	SESSION 1 Chair: Go Matsuba
9:35-9:55	The change with dispersion of silica in SBR under one-axis elongation by using time resolved USAXS method
	Shotaro Nishitsuji (Yamagata University)
9:55-10:20	Phase and crystallization behaviors of copolymer blends with hydrogen-bonding interaction
	Chieh-Tsung Lo (National Cheng Kung University)
10:20-10:45	5 Layer-by-Layer Single Crystals from Self-assembly of Triple-Crystalline Block Copolymers
	Yeo-Wan Chiang (National Sun Yat-Sen University)
	SESSION 2 Chair: Chieh-Tsung Lo
11:00-11:25	5 Formation Mechanism of the Mesoporous Silica SBA-15 Thin Sheet with Perpendicular Nanochannels
	Chung-Yuan Mou (National Taiwan University)
11:25-11:50) Effect of Coherence on Small-Angle Scattering
	Yuya Shinohara (University of Tokyo)
11:50-12:15	5 Dynamics of Glass-Formers Studied by Gamma-ray quasi-elastic scattering method Makina Saito (Kyoto University)
	SPECIAL LECTURE <i>Chair</i> : Masaaki Sugiyama
13:30-14:15	5 Boron Neutron Capture Therapy (BNCT) including

	every element of the achievements in radiation oncology since the discovery of X-ray
	Koji Ono (Kyoto University)
	SESSION 3 Chair: Hideki Seto
14:15-14:40	
	X-ray reflectivity studies on the mixed thiol capped Au nanoparticle/lipid monolayers
	Tsang-Lang Lin (National Tsing Hua University)
14:40-15:05	
	Solvated structure and phase behavior of thermo-responsive polymer in ionic liquid
	Mitsuhiro Shibayama (University of Tokyo)
15:05-15:30	
	Biological Hydrogels Formed by Swollen Multilamellar Liposomes
	Shih-Huang Tung (National Taiwan University)
	SESSION 4 Chair: Rong-Ming Ho
15:45-16:10	
	Structural characterization of poly(3,4-ethylenedioxy-2,5-thiophene):poly(styrene sulfonate) dispersions and corresponding spin-cast thin films via small-angle X-ray scattering
	An-Chung Su (National Tsing Hua University)
16:10-16:35	
	Structural Transitions of BAX after the Apoptotic Activation
	Orion Shih (National Synchrotron Radiation Research Center)
16:35-17:00	
	Surface Characterization of Poly(flruoroalkyl acrylates) by Surface X-ray Diffraction/Scattering and Neutron Reflectivity
	Atsushi Takahara (Kyushu University)
17:00-17:20	Group Photo

March 12th

SESSION 5 Chair: Wei-Tsung Chuang

9:00-9:25	
	SAXS and SANS study on the structural change of human stratum corneum induced by the treatment of surfactant solution
	Takuji Kume (Kao Corporation)
9:25-9:50	
	Small-angle neutron and X-ray scattering studies on metallocene EPDM
	Kazuki Mita (Mitsui Chemicals, Inc.)
9:50-10:15	
	Electrochemical Reaction of Carbon Film with Electrolyte Solution as Studied by Time-slicing Neutron Reflectometry
	Masashi Harada (Toyota Central R&D Labs., Inc.)
	SESSION 6 Chair: Tsang-Lang Lin
10:30-10:55	Fabrication of Perpendicular Nanoporous TiO ₂ Thin Films through Templated Synthesis of Dendron-Jacketed Block Copolymers
	Wei-Tsung Chuang (National Synchrotron Radiation Research Center)
10.55-11.20	
10.00 11.20	An Effect of Aggregation States in Nafion Thin Films on Transport Properties
	Daisuke Kawaguchi (Kyushu University)
11:20-11:45	
	Competition between Entropy and Enthalpy in the Binding of Melittin with ULV Vesicles of Different Phosphate Lipid Chain Lengths
	Chun-Jen Su (National Synchrotron Radiation Research Center)
	SESSION 7 Chair: Mikihito Takenaka
13:00-13:25	SAXS combined with crystallography for structural studies on macromolecular complexes and functional flexibility of protein
	Shu-Ying Sherry Wang (National Cheng Kung University)

13:25-13:50	
	Liquid phase networks of conjugated polymers and carbon allotropes
	Jrjeng Ruan (National Cheng Kung University)
13:50-14:15	
	Probing UV-Irradiated and pyrolyzed block copolymer micelles on a solid by grazing incident X-ray
	Ya-Sen Sun (National Central University)
	SESSION 8 Chair: U-ser Jeng
14:30-14:55	
	Dynamic quaternary structure of alpha-crystallin
	Rintaro Inoue (Kyoto University)
14.55-15.20	
11.00 10.20	The correlation between the mechanics of a lipid membrane and its cellular functions
	Yi-Fan Chen (National Central University)
15.20-15.45	
15.20-15.45	Structural insights into molecular assembly in the proteasomal systems
	Tadashi Sato (Nagoya City University)
	SESSION 9 Chair: Mistuhiro Shibayama
16:00-16:25	
	Current status and results on J-PARC/MLF
	Hideki Seto (KEK)
16.25 16.50	
10.23-10.30	Nanostructured Networks in Chiral Block Copolymers
	Rong-Ming Ho (National Tsing Hua University)
16:50-17:15	
	Hierarchical Structure of Polymer/Nanoparticle Hybrid
	Hsin-Lung Chen (National Tsing Hua University)
17:15	
	Closing Remarks

The change with dispersion of silica in SBR under one-axis elongation by using time resolved USAXS method

Shotaro Nishitsuji¹, Sho Suzuki¹ and Mikihito Takenaka²

¹ Department of Polymer Science and Engineering, Graduate School of Science and Engineering, Yamagata University

²Department of Polymer Chemistry, Graduate School of Engineering, Kyoto University

E-mail: nishitsuji@yz.yamagata-u.ac.jp

Recently, from the viewpoint of the environmental problems and the depletion of fossil fuel resources, the high performance of tire is required. To achieve more high performance, it is important to investigate the relationship between the dispersion of filler in the rubber/filler system and the improvement of the mechanical properties. In the previous studies, the hierarchical structures in the rubber/filler system have been investigated by using a combined ultra small scattering and small angle scattering method of neutrons and X-rays[1,2]. In this study, the change with the dispersion of silica in Styrene-Butadiene Rubber (SBR) with one-axis elongation by using time resolved ultra small X-ray scattering (USAXS) was investigated.

SBR/Silica systems where the silica contents are 10, 15, 20, 25 vol% is prepared. Added weight fraction of the coupling agent to all the samples is 8 wt% of silica weight. Time resolved USAXS experiment was conducted at BL19B2, SPring-8, JAPAN.

The scattering pattern at 25 % of silica content before elongation and after elongation at 200 % as shown in Figure 1. Before elongation, the scattering pattern is isotropic. However, after elongation, the scattering pattern is anisotropic and is enhanced along elongation axis. This indicates the inhomogeneity of the dispersion of silica is enhanced along the elongation direction by one-axis elongation. From the analysis by Unified Guinier/Power-law approach, several



Fig.1 Scattering pattern at 25 % of silica content (a)before elongation and (b)after elongation at 200 %.

characteristic parameters are estimated quantitatively, such as the size of aggregation and agglomerate, mass-fractal dimension. We will discuss the detail analysis by this approach and the change with the dispersion of silica in SBR quantitatively.

Acknowledgement : The samples in this study were provided from THE YOKOHAMA RUBBER CO., LTD.

References

T. Koga, M. Takenaka, K. Aizawa, M. Nakamura, T. Hashimoto, *Langmuir*, **21**, 11409 (2005).
T. Koga, T. Hashimoto, M. Takenaka, K. Aizawa, N. Amino, M. Nakamura, D. Yamaguchi, S. Koizumi, *Macromolecules*, **41**, 453 (2008).



Name: Shotaro Nishitsuji (西辻 祥太郎)

Title and Affiliation: Assistant Professor, Department of Polymer Science and Engineering, Graduate School of Science and Engineering, Yamagata University,

E-Mail: nishitsuji@yz.yamagata-u.ac.jp

- Polymer Physics
- Small Angle X-ray Scattering
- Polymer Blend

Phase and crystallization behaviors of copolymer blends with hydrogen-bonding interaction

Chieh-Tsung Lo^{*} and Yu-Wen Chen

Department of Chemical Engineering, National Cheng Kung University

E-mail: tsunglo@mail.ncku.edu.tw

We investigated the effect of the hydrogen-bonding interaction on the phase and crystallization behaviors of binary copolymer blends. In the blends composed of polystyrene-*block*-poly(ethylene oxide) (PS-*b*-PEO) and polystyrene-*block*-poly(acrylic acid) (PS-*b*-PAA) block copolymers, the hydrogen bonding between PEO and PAA improved the miscibility between the two molecules, which facilitated the localization of PS-*b*-PAA at the interface of the PS-*b*-PEO microdomains. However, the formation of hydrogen bonding decreased the crystallizable chain length of PEO, resulting in the occurrence of PEO crystallization within more confined region. As a result, the crystallization temperature of PEO decreased. By contrast, in the blends containing PS-*b*-PEO and polystyrene-*graft*-poly(acrylic acid) (PS-*g*-PAA) graft copolymer, PS-*g*-PAA was sequestered into the PEO domains, which caused swelling and increased the interfacial curvature that in turn, induced morphological transitions. Additionally, the hydrogen-bonded PEO and PAA in the PS-*b*-PEO/PS-*g*-PAA blends occurred in the middle or the free end of the PEO chains. The packing of PEO chains during crystallization was restricted by not only the chemically-linked PS-*b*-PEO interface but also the hydrogen-bonded PAA. This caused a substantial increase in the surface fold energy of PEO. As a result, a high degree of supercooling was needed to overcome the increased surface fold energy of PEO and crystallization occurred at a low temperature.



Figure 1. Schematic illustration of the phase behavior of blends with presence of hydrogen-bonding interaction. (a) PS-*b*-PEO/PS-*b*-PAA and (b) PS-*b*-PEO/PS-*g*-PAA.



Name: Chieh-Tsung Lo (羅介聰) Title and Affiliation: Professor, National Cheng Kung University

E-Mail: tsunglo@mail.ncku.edu.tw

- Polymer physics -
- -
- Polymer nanocomposites Polymer surfaces and interfaces _

Layer-by-Layer Single Crystals from Self-assembly of Triple-Crystalline Block Copolymers

Yeo-Wan Chiang*, You-Yuan Hu, Jhen-Ning Li, Shih-Hung Huang

Department of Materials and Optoelectronic Science, Center for Nanoscience and Nanotechnology, National Sun Yat-Sen University, Kaohsiung 80424, Taiwan

E-mail: ywchiang@mail.nsysu.edu.tw

Manipulation of crystalline textures of biocompatible block copolymers is critical for the applications in the medical field. Here, we present the control of multiple-crystalline morphologies with flat-on chain orientation in biocompatible poly(ethylene oxide)-*block*-poly(ϵ -caprolactone)-*block*-poly(L-lactide) (PEO-PCL-PLLA) triblock copolymer thin films using melt and solvent-induced crystallization.^[1] Only single-crystalline morphologies of the first-crystallized blocks can be obtained in the melt-crystallized thin films due to confinement effect. With solvent annealing by PCL-selective toluene, single-crystalline PLLA to double-crystalline PLLA/PCL and to triple-crystalline PLLA/PCL/PEO layered crystals in sequence are observed for the first time. With the control of solvent selectivity, different sequential crystallization involving first-crystallized PCL transferring to double-crystalline PCL/PLLA is obtained using PEO-selective *n*-hexanol for annealing. Surprisingly, the crystalline growth of the tri-layered single crystal exhibits specific layer-by-layer epitaxial relationship. As a result, the multiple-crystalline textures of the PEO-PCL-PLLA thin films can be carried out by controlling solvent and polymer interaction.

References

[1] Y.-W. Chiang,* S.-H. Huang, S.-W. Kuo, Macromolecules, 48, (2015) 8526.



Name: Yeo-Wan Chiang (蔣酉旺)

Title: Assistant Professor, Department of Materials and Optoelectronic Science, National Sun Yat-Sen University, Taiwan

E-mail: ywchiang@mail.nsysu.edu.tw

- Self-assembly of Block Copolymers and Supramolecules -
- Phase Behavior of Crystallizable Block Copolymers Block Copolymer Photonic Crystals -
- -

Formation Mechanism of the Mesoporous Silica SBA-15 Thin Sheet with Perpendicular Nanochannels

Yi-Qi Yeh¹, U-Ser Jeng¹ and Chung-Yuan Mou²

¹ National Synchrotron Radiation Research Center, Hsinchu 30076, Taiwan ² Department of Chemistry, National Taiwan University, Taipei 10617, Taiwan

E-mail: cymou@ntu.edu.tw

Mesoporous silica SBA-15 thin sheets with perpendicular nanochannels, SBA(\perp), was synthesized by using the ternary surfactant system of SDS (sodium dodecylsulfate) – CTAB (hexyltrimethylammonium bromide) – P123 (PEO₂₀-PPO₇₀-PEO₂₀).¹⁻⁴ The SBA(\perp) structural features, 2D hexagonally arrayed nanochannels, was considered deriving from the nonionic triblock copolymer P123. The SDS-CTAB system was proposed to function as a bilayer membrane to confine the co-organizing P123 and silicates. With neutron scattering, P123 displays strong scattering length density (SLD) contrast than deuterated SDS (d-SDS), deuterated CTAB (d-CTAB), and silicates in D₂O solvent. In X-ray scattering, silicates exhibits strong SLD than the surfactants. In this report, we investigated the role of P123 micellization and the co-assembly process of silicate-surfactant system to realize the SBA(\perp) formation mechanism using both SANS and SAXS.

The charge condensation effect (varing(d-SDA)/P123, R_c : 0~128.75, in SDS-CTAB-P123 surfactant template) suggested a transformation of P123 micelles from sphere to prolate. An increase in aspect ratio of prolate micelles with increasing ionic surfactant (d-SDS)/(d-CTAB) concentration until R_c 25.75. With excess ionic surfactant, the aspect ratio of the prolate would be reduced. The charge optimization effect (varying (d-SDS)/(d-CTAB)), R_o : 1.2 - 2.0, in SDS-CTAB-P123 surfactant template) showed all the micelles behaved as prolate micelle and the best recipe of R_o =1.5 exhibits the highest aspect ratio ~2.9.

The structural evolution during the co-assembly process of surfactant and silicates revealed three transitions as following: (1) The surfactant-silicate prolates would align and form lamellae phase between ionic surfactant bilayers in vesicle. (2) The surfactant-silicate prolates between two vesicles would polymerize due to hydrogen-binding of silicates. The fluctuation between the bilayer would supposedly reduce the lamellae ordering. (3) The enlogated surfactant-silicate prolates would transform into well-aligned cylinders and form 2D hexagonal mesostructured. The TEM results also support the proposed surfactant template and co-assembly processes.

References

B.C. Chen, H.P. Lin, M.C. Chao, C.Y. Mou and C.Y. Tang, *Adv Mater*. 2014, 16,1657
Y-Q. Yeh, H.P. Lin, *Langmuir* 2006, 22, 6
Y-Q. Yeh, C-Y. Tang, and C-Y. Mou, *J. Colloid Interface Sci.* 2011, 362, 354
Y-Q. Yeh, C-Y. Tang, and C-Y. Mou, *APL Mater*. 2014, 2, 113303



Name: Chung-Yuan Mou (牟中原)

Title and Affiliation: Chair Professor, Department of Chemistry, National Taiwan University

E-Mail: cymou@ntu.edu.tw

- Catalytic oxidation by gold nanoparticles
- Nanoporous nanomaterials as a drug/enzyme delivery carrier in Biomedicine
- Studies of supercooled confined water

Effect of Coherence on Small-Angle Scattering Yuya Shinohara and Yoshiyuki Amemiya

Department of Advanced Materials Science, Graduate School of Frontier Sciences, The University of Tokyo

E-mail: yuya@k.u-tokyo.ac.jp

Coherence is a fundamental concept for discussing scattering phenomena. Despite its importance, it is mostly ignored in the textbook of scattering of X-rays and neutron. Recent progress in X-ray brilliance makes it possible to conduct experiments utilizing coherence of X-rays: coherent diffraction imaging for the real-space visualization of materials' structure and X-ray photon correlation spectroscopy for monitoring the dynamics of nano-scale. In these techniques, the concept of coherence is explicitly utilized.

We have recently realized that the coherence may affect the scattering intensity profiles even when the incident X-ray is not fully coherent [1]. According to standard textbooks of small-angle scattering, scattering intensity profiles correspond to the fluctuation part of scattering length density, while a forward scattering at q = 0 is not explicitly considered, where q is the magnitude of scattering vector. Recent advances in X-ray brilliance and X-ray optics make it possible to conduct scattering measurement at ultra-small angles with a small beam size. We have found that the measurement at such a low q leads to a significant contribution from the forward scattering on the measured scattering intensity profiles. The degree of contribution depends on the coherent length of incident X-rays, regardless of whether the beam is fully coherent or not. In this presentation, we will discuss the effect of coherence on small-angle scattering and perspectives on ultra-small-angle scattering.

References

[1] Y. Shinohara and Y. Amemiya, J. Appl. Cryst., 48, (2015) 1660-1664.



Name: Yuya Shinohara (篠原 佑也)

Title and Affiliation: Assistant Professor, Department of Advanced Materials Science, Graduate School of Frontier Sciences, The University of Tokyo

E-Mail: yuya@k.u-tokyo.ac.jp

Research Interests:

- Development of X-ray scattering technique

Dynamics of Glass-Formers Studied by Gamma-ray quasi-elastic scattering method

Makina Saito¹, Makoto Seto¹, Ryo Masuda¹, Yasuhiro Kobayashi¹, Shinji Kitao¹, Masayuki Kurokuzu¹ and Yoshitaka Yoda²

¹Research Reactor Institute of Kyoto University ²Japan Synchrotron Radiation Research Institute

E-mail: msaito@rri.kyoto-u.ac.jp

When liquids are cooled toward the glass transition temperature avoiding crystallization, the microscopic relaxation time or viscosity, in some cases, changes more than 10 orders of magnitude in a narrow temperature range without an apparent structural change. Understanding the mechanism is one of the most important aim of the glass transition study. A relaxation process known as the α process, which is the structural relaxation process associated with the molecular diffusion, is directly related to the dynamical behaviour. With cooling the liquid, the other relaxation process emerges as its relaxation time branches from the relaxation time of the α process. The process is called the slow β (Johari–Goldstein) process and its origin is still controversial. The branching process seems to be a key to understand the glass transition and the molecular dynamics in deeply supercooled liquids.

To examine the decoupling phenomenon from the microscopic point of view, a typical glass formers *o*-terphenyl [1] and polybutadiene have been studied [2] by the quasi-elastic scattering measurement known as a time-domain interferometry (TDI) method using gamma rays from ⁵⁷Fe nucleus excited by synchrotron radiation [3]. This method is a time-domain analogue of the conventional Rayleigh scattering Mössbauer radiation method [4]. Generally by a quasi-elastic scattering method, the relaxation time of microscopic structures with a certain microscopic length scale $l\sim 2\pi/q$ can be selectively studied, where q is the momentum transfer of the gamma ray to the liquid sample decided by selecting the scattering angle of the detector. Owing to the atomic wavelength of the ⁵⁷Fe gamma-ray ~ 0.087 nm (corresponding energy ~ 14.4 keV) and its relatively narrow energy width ~ 4.7 neV, the atomic and molecular dynamics can be studied in the time range of ns ~ μ s. We introduce a new result obtained by the TDI method on the glass formers.

References

[1] M. Saito, S. Kitao, Y. Kobayashi, M. Kurokuzu, Y. Yoda and M. Seto, *Phys. Rev. Lett.*, 109, (2012) 115705.

[2] T. Kanaya, R. Inoue, M. Saito, M. Seto, and Y. Yoda, J. Chem. Phys., 140, (2014) 144906.

[3] A. Q. R. Baron, H. Franz, A. Meyer, R. Rüffer, A. I. Chumakov, E. Burkel and W. Petry, *Phys. Rev. Lett.*, 79, (1997) 2823.

[4] D. C. Champeney and F. W. D. Woodhams, J. Phys. B., 1, 1620 (1968) and references therein.



Name: Makina Saito (齋藤 真器名)

Title and Affiliation: Assistant Professor, Research Reactor Institute, Kyoto university

E-Mail: msaito@rri.kyoto-u.ac.jp

- Topic 1 Quasi-elastic scattering _
- Topic 2 Glass transition phenomenon Topic 3 Soft matter _
- _

Boron Neutron Capture Therapy (BNCT) including every element of the achievements in radiation oncology since the discovery of X-ray

Koji Ono

Research Reactor Institute, Kyoto University

E-mail:onokoji@rri.kyoto-u.ac.jp

When the history of radiotherapy is traced, the achievements are summarized as below.

- Focusing of the radiation dose on the tumor definitely increase the cure rate of tumor without increasing the incidence and grade of adverse effects. The success by brachytherapy, treatment by small radioactive source, is the solid evidence. This paradigm was also proved by IORT(<u>intraoperative radiotherapy</u>), stereotactic RT, conformal RT, IMRT(intensity modulated RT), charged heavy particle therapy et al.
- 2. Physiologically moving organs like as the tongue were also treated successfully by brachytherapy. To recreate this success in an external RT, the machine of which the X-ray beam can track the moving tumor in the target organ on respiration, was developed in Japan.
- 3. High LET radiation is very effective for the tumors which are refractory to X-rays. Carbon ion therapy was prove to successfully treat the soft tissue tumor or bone sarcomas which are radioresistant to X-rays. as the tumour cell selective cancer therapy

BNCT includes every element of these achievements. The idea of BNCT was proposed in 1932 based on the feature of ${}^{10}B(n,\alpha)^7Li$ reaction. The cross section of this reaction is 2000 times larger than that of ${}^{14}N(n,p){}^{14}C$ reaction. Moreover the particles have extremely short ranges which are shorter than the diameter of general cells, hence, these particles destroy the tumour cells selectively if ¹⁰B accumulates in tumour cells selectively. The particles are also high LET radiation and then have large RBE (relative biological effectiveness). The first clinical study started in 1951 in US after the 2nd World War because the nuclear reactor was necessary as a neutron source. Unfortunately this trial failed to indicate the benefit of BNCT. The clinical research was succeeded by Japanese researchers since 1968. They used better ¹⁰B-compound, BSH, and achieved fairly nice result. It was 1987 when the clinical BNCT changed dramatically. BPA appeared as the clinically applicable 2nd ¹⁰B-compound this year. BPA actively accumulates in cancer cells, with that, BNCT has become cancer selective treatment in true meaning. Development of ¹⁸F-BPA PET(positron emission tomography), proposal of CBE(compound biological effectiveness) factor, success of BNCT for the recurrent H & N cancer, the world's first cyclotron based neutron source for clinical BNCT and start of the clinical test in 2012 were major progresses of BNCT since the appearance of BPA. Many of these achievements were developed by KURRI researchers and their colleagues. BNCT seems to be a completed form of radiotherapy.



Name: Koji Ono (小野 公二)

Title and Affiliation: Professor, Research Reactor Institute, Kyoto University

E-Mail: onokoji@rri.kyoto-u.ac.jp

- BNCT
- Radiation Oncology
- Radiation Biology

X-ray Reflectivity Studies on the Mixed Thiol Capped Au Nanoparticle/Lipid Monolayers

Tsang-Lang Lin¹, Han-Shiou Su¹, Yi-Tang Chen¹, Chin-Hua Hung¹, Yuan Hu¹, Ming-Tao Lee², U-Ser Jeng²

¹ Department of Engineering and System Science, National Tsing Hua University, Hsinchu, Taiwan 30013, R.O.C.

² National Synchrotron Radiation Research Center (NSRRC), Hsinchu, Taiwan, R.O.C.

E-mail: tllin@mx.nthu.edu.tw

The Langmuir-Blodgett films of thiol capped gold nanoparticles mixed with zwitterionic lipid, dipalmitoylphosphatidylcholine (DPPC), were investigated by X-ray reflectivity, grazing-incident scattering, and transmission electron microscopy (TEM). The synthesized gold nanoparticles have an average diameter around 2 nm, and the gold nanoparticles were capped with 1-propanethiol, 1-octanethiol and 1-dodecanethiol, respectively. The monolayers were transferred onto silicon wafers for X-ray analysis and onto copper grid for TEM analysis. As revealed by X-ray reflectivity, for the mixed 1-octanethiol capped Au nanoparticle/DPPC monolayer system, at low compression pressure, the 1-octanethiol capped Au nanoparticles form a monolayer on top of disordered lipid monolayer. When the surface pressure is increased, the disordered lipid monolayer becomes ordered and the 1-octanethiol capped Au nanoparticle monolayer stays on top of it. It is favorable for the hydrophobic thiol capped Au nanoparticles to sit on the hydrophobic lipid tails instead of staying at the water surface. It seems that thiol capped Au nanoparticles have strong affinity to form large closely packed domains on smooth hydrophobic surface. Since the thiol capped Au nanoparticles would prefer to stay on top of the lipid monolayer to avoid contacting with water, it would be difficult to disperse the thiol capped Au nanoparticles into the lipid monolayer. We also investigated the morphology of these three thiol capped Au nanoparticle monolayers. At compression pressure of 20 mN/m, the 1-propanethiol capped Au nanoparticles tend to form multiply folded layers as revealed by TEM, while the 1-dodecanethiol capped Au nanoparticles form monolayers in grains with thread-like thiol-capped Au nanoparticle clusters forming the grain boundaries. It seems that the 1-dodecanethiol capped Au nanoparticle monolayer has better stability again compression as compared with the 1-propanethiol capped Au nanoparticle monolayer.



Name: Tsang-Lang Lin (林滄浪)

Title: Professor, National Tsing Hua University

E-Mail: tllin@mx.nthu.edu.tw

- Colloids and interfaces
- Nanomaterials and biomaterials
- Neutron and X-ray scattering

Solvated Structure and Phase Behavior of Thermo-responsive Polymer in Ionic Liquid

Mitsuhiro Shibayama¹, Kazu Hirosawa¹, Kenta Fujii², Takeshi Ueki, ³Yuzo Kitazawa,⁴ Ken Littrell⁵ and Masayoshi Watanabe⁴

¹Institute for Solid State Physics, The University of Tokyo, ²Graduate School of Science and Engineering, Yamaguchi University, ³Polymer Materials Unit, National Institute for Materials Science, ⁴Department of Chemistry and Biotechnology, Yokohama National University, ⁵Oak Ridge National Laboratory

E-mail: sibayama@issp.u-tokyo.ac.jp

Ionic liquids (ILs) consist of only ion species, and thus, they have unique solvent property such as high ion conductivity, electrochemical stability, nonvolatility and nonflammability. In polymer science, the combination of polymer materials with ILs permits the fabrication of functional soft materials possessing the unique properties of ILs. Recently, stimuli-responsive polymers in ILs have been developed and received a great deals of attention.¹ For example, poly(benzyl methacrylate) (PBnMA) and its derivatives show lower critical solution temperature (LCST) – type phase separation in hydrophobic IL ([C₂mIm⁺][TFSA⁻]), and their phase-separating temperature (T_c) can be drastically changed by slight chemical modification on the side chain.² We performed small-angle neutron scattering (SANS) study on one of the PBnMA derivatives, PPhEtMA (poly(2-phenylethyl methacrylate)) in ionic liquid.

SANS experiments were carried out for PPhEtMA in deuterated ionic liquid, d_8 -[C₂mIm⁺][TFSA⁻] at High-Flux Isotope Reactor in Oak Ridge National Laboratory, USA. d_8 -[C₂mIm⁺][TFSA⁻] was prepared by the procedure well established in our research group. Fig. 1 shows the SANS profiles obtained for PPhEtMA in d_8 -[C₂mIm⁺][TFSA⁻] at various temperatures, 288 K - 310 K. As can be seen from the figure, steep upturn was observed when temperature exceeded T_c (~ 309 K in d_8 -[C₂mIm⁺][TFSA⁻]), indicating the appearance of large aggregates in this region. We evaluated the second virial coefficient, A_2 by Zimm plot. The obtained A_2 decreased and changed its sign from positive to negative with increasing temperature. The result indicated compatibility **PPhEtMA** that of into d_8 -[C₂mIm⁺][TFSA⁻] decrease gradually with increasing temperature.



Figure. 1 SANS profiles observed for PPhEtMA / d_8 -[C₂mIm⁺][TFSA⁻] solution at various temperature. The solid lines shows the fitting results by the Debye or Debye + Squared Lorentz functions.

References

[1] T. Ueki, Polym. J., 1 (2014). [2] K. Kodama et al., Langmuir, 25, 3820 (2009).



Name: Mitsuhiro Shibayama (柴山 充弘)

Title and Affiliation: Professor, The University of Tokyo

E-Mail: sibayama@issp.u-tokyo.ac.jp

- Structure characterization of hydrogels and ionic gels Structure of polymer micelles Molecular dynamics of thermosets -
- -
- _

Biological Hydrogels Formed by Swollen Multilamellar Liposomes

Chih-Yang Cheng,¹ Ting-Yu Wang,² and Shih-Huang Tung¹

¹Institute of Polymer Science and Engineering and ²Instrumentation Center, National Taiwan University, Taipei, 10617 Taiwan

E-mail: shtung@ntu.edu.tw

The self-assembly of lecithin-bile salt mixtures in solutions has long been an important research topic, not only because they are both biosurfactants closely relevant to physiological functions but also for the potential biomedical applications. In this paper, we report an unusual biological hydrogel formed by mixing bile salts and lecithin at low bile salt/lecithin molar ratios (B_0) in water. The gel can be prepared at a total lipid concentration as low as ~ 15 wt% and the solid-like property of the solutions was confirmed by dynamic rheological measurements. We used cryo-TEM and SAXS/SANS techniques to probe the self-assembled structure and clearly evidence that the gel is made up of jammed swollen multilamellar vesicles (liposomes), instead of typical fibrous networks found in conventional gels. A mechanism based on the strong repulsion between bilayers due to the incorporation of negatively charged bile salts is proposed to explain the swelling of the liposomes. In addition to gel, a series of phases, including viscoelastic, gel-like, and low-viscosity fluids, can be created by increasing B_0 . Such a variety of phase behaviors are caused by the transformation of bilayers into cylindrical and spheroidal micelles upon the change of the effective molecular geometry with B_0 .



References

C.-Y. Cheng, T.-Y. Wang, and S.-H. Tung, *Langmuir*, 31, (2015) 13312-13320.
C.-Y. Cheng, H. Oh, T.-Y. Wang, S. R. Raghavan, and S.-H. Tung, *Langmuir*, 30, (2014) 10221-10230.



Name: Shih-Huang Tung (童世煌)

Title and Affiliation: Associate Professor, National Taiwan University

E-Mail: shtung@ntu.edu.tw

- Self-assembly and phase behaviors of block copolymers Self-Assembly of amphiphilic biomolecules Rheology of complex fluids -
- _
- _

Structural characterization of poly(3,4-ethylenedioxy-2,5-thio phene):poly(styrene sulfonate) dispersions and corresponding spin-cast thin films via small-angle X-ray scattering

Jia-Jhen Kang,¹ Hung-Ting Chen,¹ Wei-Ru Wu,² U-Ser Jeng,^{1,2} and An-Chung Su¹

¹ Department of Chemical Engineering, National Tsing Hua University, Hsinchu 30013, Taiwan ² National Synchrotron Radiation Research Center, Hsinchu Science Park, Hsinchu 30076, Taiwan

E-mail: acsu@mx.nthu.edu.tw

Structural features of aqueous poly(3,4-ethylenedioxy-2,5-thiophene):poly(styrene sulfonate) (PEDOT:PSS) dispersions with the PPS-to-PEDOT mass ratio r = 2.5 or 6.0 in the concentration range of 0.2–1.2 wt% were characterized by means of small-angle X-ray scattering (SAXS). Results indicate that these dispersions generally comprise prolate nano-ellipsoids (with aspect ratio $v \approx 5$) of aggregated PEDOT segments encircled by swollen coronae of anchored PSS chains. A major fraction ($\phi_P \approx 0.9$) of these micelles are uniformly distributed in the aqueous matrix according to disordered packing of hard spheres. A minor fraction ($\phi_F < 0.1$) of these micelles loosely inter-connect into domains of fractal dimension $D_F \approx 1.9$. There are also a minor fraction ($\phi_0 < 0.1$) of micelles with oblate core of $v \approx 0.6$, which corresponding to lateral agglomerates of the "normal" prolate cores. With increasing polymer concentration, ϕ_F decreases whereas ϕ_0 increases, especially for the lower PSS content case of r = 2.5. This trend of agglomeration into oblate PEDOT cores with increasing polymer concentration extends into spin-cast films, where grazing-incidence small-angle X-ray scattering (GISAXS) profiles generally indicate interconnected prolate ellipsoids into fractal domains of $D_F \approx 2.5$ but more significant presence ($\phi_0 \approx 0.2-0.3$) of oblate PEDOT-rich domains, especially for the case of r = 2.5.



Name: An-Chung Su (蘇安仲)

Title and Affiliation: Professor of Chemical Engineering, National Tsing Hua University

E-Mail: acsu@mx.nthu.edu.tw

- Structure-property relationship in polymeric systems Semiconducting polymers -
- -
- Nanomaterials _

Structural Transitions of BAX after the Apoptotic Activation Orion Shih¹, Yi-Qi Yeh¹, Tai-Ching Sung², Yun-Wei Chiang² and U-Ser Jeng¹

¹ National Synchrotron Radiation Research Center, Hsinchu 30076, Taiwan ² Department of Chemistry, National Tsing-Hua University, Hsinchu 30013, Taiwan

E-mail: shih.orion@nsrrc.org.tw

In stressed cells, apoptosis ensues when BAX proteins oligomerize and permeabilize the mitochondrial outer membrane [1]. The mechanism utilized by BAX still remains elusive because BAX changes its functional structures along the apoptotic signaling pathway from cytosolic monomer, oligomer, to membrane-associated complex. This polymorphism of BAX poses a great challenge in tracing its structural transitions in functioning. Here we use a combination of electron spin resonance (ESR) and small angle X-ray scattering (SAXS) to study the conformational changes of BAX before and after the apoptotic activation. Particularly, an on-line HPLC is used to separate the BAX monomers, dimers, and oligomers in the eluted sample solution along the flow path for in-situ SAXS data collection at the 23A SWAXS endstation of National Synchrotron Radiation Research Center, Hsinchu, Taiwan [2].

The HPLC elution profile and previous ESR studies [3] indicate that there exist two forms of BAX monomer, UM and UM'. Upon the engagement of BimBH3, UM and UM' are transformed into a ligand-bound monomer (BM) and a oligomer (O), respectively. We construct the solution structures of BAX along the oligomerization pathway and show that BAX oligomers are assembled in solution via linear polymerization-like $\alpha 6$ association. Our results specifically establish oligomerization interfaces and intermediates, which are important structural basis for manipulating BAX activity pharmacologically.

References

[1] Antonsson, B., Montessuit, S., Sanchez, B., and Martinou, J. C. J. Biol. Chem. 276, (2001) 11615-11623.
[2] Jeng, U., Su, C., Su, C., Liao, K., Chuang, W., Lai, Y., Chang, J., Chen, Y., Huang, Y., Lee, M., Yu, K., Lin, J., Liu, D., Chang, C., Liu, C., Chang, C., and Liang, K. S. J. Appl. Cryst. 43, (2010) 110–121.
[3] Tsai, C., Liu, S., Hung, C., Jhong, S., Sung, T. and Chiang, Y. Structure 23, (2015) 139-148.



Name: Orion Shih (施怡之)

Title and Affiliation: Postdoc, NSRRC

E-Mail: shih.orion@nsrrc.org.tw

- SAXS from biological macromolecules NEXAFS of liquid microjets -
- _

Surface Characterization of Poly(flruoroalkyl acrylates) by Surface X-ray Diffraction/Scattering and Neutron Reflectivity Atsushi Takahara^{1,2}

¹Institute for Materials Chemistry and Engineering, Kyushu University, ²International Institute for Carbon-Neutral Energy Research (WPI-I2CNER) Kyushu University

takahara@cstf.kyushu-u.ac.jp

Polymers with fluoroalkyl (R_f) groups are attractive to a broad range of applications in the paint and coatings sector. Surface properties of the fluoropolymers with perfluoroalkyl (R_f) side groups depend on the surface molecular aggregation structure and surface molecular motion. Surface molecular aggregation structure and surface molecular motion. Surface molecular aggregation structure and surface molecular motion of the poly(fluoroalkyl acrylate) (PFA-C_y, where y is the fluoromethylne number of the R_f groups) and poly(fluoroalkyl methacrylate) (PFMA-C_y) were investigated by grazing incidence wide-angle X-ray diffraction (GI-WAXD) measurement, temperature dependence of the dynamic contact angle measurement, X-ray photoelectron spectroscopy (XPS) measurement in pseudo-hydrated state, and lateral force microscopy (LFM) measurement [1-3]. It was revealed that crystallization of FA side chain at the air interface contribute to the stable surface hydrophobicity of PFA-C_y and PFMA-C_y.

We utilized scattering length density contrast of fluoroalkyl group for neutron reflectivity(NR). The plasticization effects of compressed CO₂ gas on the semicrystalline poly(FA-C₈) brush thin films (40 nm in thickness) grafted-from Si substrates were studied by NR[4]. In *situ* NR measurements were performed under the isothermal condition of T = 309 K ($<< T_m$). The results showed the significant increase in the swelling of the polymer brush with increasing CO₂ pressure. This indicates that the large sorption of CO₂ molecules induces the melting of the semicrystalline poly(FA-C₈) brush at P > 4.1 MPa.

This work was partially supported by the Photon and Quantum Basic Research Coordinated Development Program of MEXT, Japan

References

[1] K. Honda, M. Morita, H. Otsuka, A. Takahara, *Macromolecules*, 38, (2005) 5699.

[2] K. Honda, H. Yakabe, T. Koga, S. Sasaki, O. Sakata, H. Otsuka, A. Takahara, *Chem. Lett.*, 34, (2005) 1024.

[3] K. Honda, M. Morita, O. Sakata, S. Sasaki, A. Takahara, *Macromolecules*, 43, (2010) 454.

[4] H. Yamaguchi, P. Gin, H. Arita, M. Kobayashi, S. Bennett, S. K. Satija, M. Asada, T. Koga, A. Takahara., *RSC Adv.*, 3, (2013) 4778.



Name: Atsushi Takahara (高原 淳)

Title and Affiliation: Director and Professor, Institute for Materials Chemistry and Engineering, Kyushu University

E-Mail: takahara@cstf.kyushu-u.ac.jp

- Polymer Surface and Interfaces
- Nanocomposites
- Quantum Beam Analysis

SAXS and SANS study on the structural change of human stratum corneum induced by the treatment of surfactant solutions

Takuji Kume¹, Makoto Onoo¹ and Ichiro Hatta²

¹Kao Corporation ² Nagoya Industrial Science Research Institute

E-mail: kume.takuji@kao.co.jp

The outermost layer of the skin, stratum corneum (SC) consists of corneocytes and intercellular lipid matrix, as shown schematically in Figure 1. The structure of the SC plays an important role in the barrier function [1, 2]. The surfactant used in skin cleansers sometimes induces swellings of SC. They are accompanied by structural changes of keratin fibers in the corneocytes, and the changes of intercellular lipids lamellar structure around the corneocytes. The aim of this research is to study the conformation change of human SC, particularly the soft keratin conformation, induced by the treatment of surfactant solutions using scattering analysis.

A problem emerged while conducting small-angle X-ray scattering (SAXS) measurements – the scattering of the surfactant micelles disturbed the observation of keratin fibers, particularly microfibril structures. To resolve this problem, the influence of the scattering of surfactant micelles was eliminated by using deuterated surfactant solutions in the small-angle neutron scattering (SANS) measurements, and observing only keratin fibers in the heel SC powder (without the intercellular lipids lamellar structures) was became possible [3]. Using this technique, we analyzed the swelling of the keratin fibers in SC powder soaked with the surfactant solution of various conditions.

On the other hand, since the SANS measurement required long time, several hours per one scan, it was difficult to pursue SC structural change in a short time (from several minutes to 1 hour) after surfactant solution soak. Therefore, the SC internal structure change was measured by SAXS for a short time using the structural orientation in the stacked SC sheets. And the SAXS measurement results after prolonged progress were compared with the SANS measurement results.



Figure 1. Schematic diagram of stratum corneum (SC) structure in the human skin

References

- [1] S. H. White et al., Biochemistry, 27, (1988) 3725.
- [2] J. A. Bouwstra et al., Biochim. Biophys. Acta, 1212, (1994) 183.
- [3] T. Kume et al., Hamon, 24, (2014) 15.



Name: Takuji Kume (久米 卓志)

Title and Affiliation: Dr., Analytical Science Research Labs. Kao Corporation

E-Mail: kume.takuji@kao.co.jp

- Colloid and surface chemistry
- Soft matter
- SAXS and SANS

Small-angle neutron and X-ray scattering studies on metallocene EPDM

Kazuki Mita¹, Kiminori Uchida¹, Keisuke Shishido¹, Mitsunao Arino¹, Yoshiharu Kikuchi¹, Kotaro Ichino¹

¹Mitsui Chemicals, Inc.

E-mail: Kazuki.Mita@mitsuichemicals.com

Linear ethylene-propylene-diene terpolymers (EPDM) and those having branch structures were obtained by metallocene catalysts, and network structures of the EPDMs crosslinked by peroxide initiated reactions were investigated by small-angle neutron scattering (SANS) and small-angle X-ray scattering (SAXS). The neutron experiment at the BL20 Materials and Life Science Experimental Facility of J-PARC was performed under a user program (Proposal No. 2014AM0009). The synchrotron radiation experiments were performed at the BL03XU SPring-8 with the approval of the Japan Synchrotron Radiation Research Institute (JASRI) (Proposal No. 2013B7266, 2015A7216).



Name: Kazuki Mita (三田 一樹)

Title and Affiliation: Dr., Mitsui Chemicals, Inc.

E-Mail: Kazuki.Mita@mitsuichemicals.com

- -
- Polymer physics Crystal and network structures Small-angle scattering -
- _

Electrochemical Reaction of Carbon Film with Electrolyte Solution as Studied by Time-slicing Neutron Reflectometry

M. Harada¹, H. Kawaura¹, Y. Kondo¹, H. Kondo¹, Y. Suganuma¹,

N. Takahashi¹, J. Sugiyama¹, Y. Seno¹, N. L. Yamada²

¹Toyota Central R&D Labs., Inc., ²KEK

E-mail: harada@mosk.tytlabs.co.jp

Safety and durability of lithium ion batteries (LIBs) should be improved by understanding the nature of the solid-electrolyte interphase (SEI) that is formed at the boundary between the electrode and the electrolyte in LIBs. Thus, we have measured neutron reflectivity (NR) for an interface between a carbon film and a lithium-salt solution in a purpose-built half-cell under in-situ conditions.

The electrochemical reaction was conducted by linear sweep voltammetry from the open circuit voltage, 2.9 V, to 0.05 V against Li/Li⁺. When the potential fell below around 1.0 V at a rate of 0.2 mV/s, gradual change was observed for the spectra of NR. By fitting the time-sliced NR spectra with calculated curves using a series of scattering length density (SLD) profiles, time evolution of the profiles is demonstrated as shown in Figure 1. Beside a decrease in SLD of carbon layer, growth of a thin layer was found at the interface between the carbon and the solution, as the potential decreased down from 1.0 V. The SLD of the thin layer increased by 130 %, and the layer thickened from 20 to 42 nm. While the decrease in the SLD of the C film is attributed to the lithium insertion, the growth of thin layer could be assigned to the formation of the SEI. Although the composition of the SEI cannot be analysed only by NR experiments, we can estimate that the SEI should be the reaction products of the lithium electrolyte solution with less hydrogen and lithium atoms having negative scattering length.



Figure 1 Evolution of the scattering length density profiles by decreasing the potential. Growth of SEI is observed at the interface of the carbon and the solution.



Name: Masashi Harada (原田 雅史) Title and Affiliation: Dr., Toyota Central R&D Labs., Inc

E-Mail: harada@mosk.tytlabs.co.jp

- Thin polymer film _
- _
- Colloidal dispersion Semi-crystalline polymer -

Fabrication of Perpendicular Nanoporous TiO₂ Thin Films through Templated Synthesis of Dendron-Jacketed Block Copolymers

Wei-Tsung Chuang¹, Yen-Ming, Hsu², Ya-Sen Sun², U-Ser Jeng¹, Chun-Jen Su¹

¹ National Synchrotron Radiation Research Center, Taiwan ²Department of Chemical and Materials Engineering, National Central University, Taoyuan, Taiwan

E-mail: weitsung@nsrrc.org.tw

Direct template synthesis of highly density nanoporous conversion into TiO_2 (or metal oxides) is a challenge task for maintaining thermally robust and well-ordered framework. In this study we report a unique structural transformation process for perpendicular orientation of cylindrical microdomains in Dendron-Jacketed Block Copolymers (DJBCP)¹⁻³ and design a DJBCP-template synthesis for TiO_2 films consisting of high-density nanoporous anatase with perpendicular porosity. In order to understand the mechanism of the perpendicular orientation, we investigated time-resolved structural evolution of the doctor blade-cast films annealed at 150 °C using by GISAXS, AFM and TEM measured *ex situ*. The thin films of perpendicular cylinders can be fabricated into TiO_2 nanopores via a designed DJBCP-templated synthesis. This is a straightforward and cost-effective route to create large-area well-order 1D nanostructures for applications in optics, electronic, sensing, drug delivery, separation and nanolithography, because vertically aligned 1D nanostructures could potentially improve the charge-collection efficiency and effectively increase diffusion of guest species form outside.

References

[1] Wei-Tsung Chuang, Ting-Ya Lo, Yen-Chih Huang, Chun-Jen Su, U-Ser Jeng, Hwo-Shuenn Sheu, and Rong-Ming Ho *Macromolecules*, 47, (2014), 6047-6054.

[2] Wei-Tsung Chuang, Yen-Chih Huang, Chun-Jen Su, U.-Ser Jeng and Hwo-Shuenn Sheu, *Soft Matter*, 8, (2012) 11163-11168.

[3] Wei-Tsung Chuang, H. S. Sheu, U. S. Jeng, J. J. Lee, H. H. Wu and P. D. Hong Chem. Mater., 21, (2009), 975-978.



Name: Wei-Tsung Chuang (莊偉綜)

Title and Affiliation: Assistant Research Scientist, National Synchrotron Radiation Research Center

E-Mail: weitsung@nsrrc.org.tw

- Structure and phase transitions in soft materials
- Polymer crystallization
- Block copolymer self-assembly

An Effect of Aggregation States in Nafion Thin Films on Transport Properties

D. Kawaguchi¹, Y. Ogata², N. L. Yamada³ and K. Tanaka²

¹ Education Center for Global Leaders in Molecular Systems for Devices, Kyushu University ² Department of Applied Chemistry, Kyushu University ³ Neutron Science Laboratory, High Energy Accelerator Research Organization

E-mail: d-kawaguchi@cstf.kyushu-u.ac.jp

Nafion has been widely used as a proton exchange membrane in polymer electrolyte fuel cells (PEFC). Excellent electrochemical and mechanical properties of Nafion are associated with the characteristic network structure of the hydrated phase. Although downsizing PEFC is one of the interesting developments in the near future, it appears to us that most studies for Nafion conducted so far are limited to bulk systems. In this study, aggregation states, water sorption and proton conductivity in Nafion thin films prepared on quartz substrates were examined.

A Nafion thin film was prepared on a quartz substrate by spin-coating from Nafion dispersion in the water/alcohol mixture. The film was dried under vacuum at 313 K for 20 h and then immersed into D_2O for 5 h to reach an equilibrium swollen state. A density profile of the film normal to the D_2O interface was examined by neutron reflectivity (NR) measurement using Soft

Interface Analyzer (SOFIA) at J-PARC.

Figure 1(a) shows a NR curve of the Nafion thin film in D_2O . The solid line denotes the best-fit calculated reflectivity to the experimental one based on the model scattering density (*b*/*V*) profile shown in Figure 1(b). The model containing interfacial multi-layers with a total thickness of ca. 5 nm gave a better fitting for the experimental data. The interfacial layers having lower and higher (*b*/*V*) values than the internal region correspond to the hydrophobic and D_2O -contained hydrophilic ones, respectively. This result clearly indicates that multi-layer structure was formed at the substrate interface. This may be due to the strong interaction between sulfonate groups in Nafion and quartz surface. The interfacial structure would affect the water sorption¹ and proton conductivity in Nafion thin films. We will show results in the presentation.

Reference

[1] Y. Ogata, D. Kawaguchi, N. L. Yamada, K. Tanaka, *ACS Macro Lett*, **2**, (2013) 856.



Figure 1. (a) Neutron reflectivity curve for a Nafion thin film on quartz substrate in D_2O . Experimental data set is shown by symbol. The best-fit calculated curve using a model (b/V) profile shown in (b) is



Name: Daisuke Kawaguchi (川口 大輔)

Title and Affiliation: Associate Professor, Kyushu University

E-Mail: d-kawaguchi@cstf.kyushu-u.ac.jp

- Polymer thin films and interfaces
- Molecular motion of polymers

Competition between entropy and enthalpy in the binding of melittin with ULV vesicles of different phosphate lipid chain lengths

Chun-Jen Su¹, Wei-Ru Wu¹, Wei-Tsung Chuang,¹ Yen-Chih Huang,¹ Po-Wei Yang¹, Po-Chang Lin, Chun-Yu Chen,¹ Kung-Hwa Wei², Chih-Ming Liu,² An-Chung Su³ and U-Ser Jeng^{1,3,*}

¹National Synchrotron Radiation Research Center, Hsinchu Science Park, Hsinchu 30076, Taiwan ²Department of Materials Science and Engineering, National Chiao Tung University, Hsinchu 30010, Taiwan

³Department of Chemical Engineering, National Tsing Hua University, Hsinchu 30013, Taiwan

E-mail: su.cj@nsrrc.org.tw

Concomitant polymer crystallization and nanoscale phase separation during spin-coating of polythiophene/fullerene films for polymer solar cells (PSCs) are traced using simultaneous grazing incidence small- and wide-angle X-ray scattering. The corresponding film thinning behavior observed using time-resolved UV–Vis reflectance reveals features of shear-flow-enhanced sol–gel transition and transient layering from vertical phase separation during the spin-coating process. The correlated results suggest that local phase separation, accelerated-nucleation-based polymer crystallization and fullerene aggregation, is initiated primarily within a surface layer developed during the sol–gel transition. Subsequently, the structural development is pinned, leaving only constant solvent dissipation through the surface layer until final film coarsening. The hence kinetically trapped network structure, featuring dispersed P3HT crystallites and PCBM nano-aggregates, guides the subsequent development over the optimized bulk-heterojunction structures of the spin-coated film. The shear-flow-enhanced surface layering process is a previously missing piece of information in our integrated understanding of the PSC film-formation process during spin-coating.

References

[1] Wu, W.-R., Jeng, U., Su, C.-J., Wei, K.-H., Su, M.-S., Chiu, M.-Y., Chen, C.-Y., Su, W.-B., Su, C.-H. & Su, A.-C. *ACS Nano* 5, (2011) 6233–6243.



Name: Chun-Jen Su (蘇群仁)

Title and Affiliation: Assistant Researcher, National Synchrotron Radiation Research Center

E-Mail: su.cj@nsrrc.org.tw

- Biopolymer self-assembled structure
- Polymer physics
- Small-angle x-ray scattering

SAXS combined with crystallography for structural studies on macromolecular complexes and functional flexibility of protein

Shu-Ying Wang¹, U-Ser Jeng², Michal Hammel³, and Xinquan Wang⁴

¹Dept. of Microbiology and Immunology, National Cheng Kung University, Tainan, Taiwan
²National Synchrotron Radiation Research Center, Hsinchu, Taiwan
³Lawrence Berkeley National Laboratory, Berkeley, CA, USA
⁴Center for Structural Biology, Tsinghua University, Beijing, China

E-mail: sherry523@gmail.com

The understanding of interactions between biological molecules is essential to comprehend the cellular processes in living organisms. Crystallography is a powerful tool to provide the interactive schemes of macromolecular complexes at atomic level. However, it is sometimes challenging and time consuming to crystallize large molecular machines. In this talk, I will present our work that combines crystallography and small-angle X-ray scattering (SAXS) to resolve the structures and functions of protein-DNA and protein-protein complexes. First, I will introduce our study on the peroxide response regulator PerR, a member of ferric uptake regulator (Fur) family, from *Streptococcus pyogenes*. We determined the crystal structure of PerR and resolved the first molecular architecture of PerR-DNA complex by SAXS analysis, revealing a unique DNA-binding topology distinct from currently proposed DNA-binding models for Fur family [1]. Second, I will introduce the work for studying the interactions between IL-1 cytokine members and their receptors. The activation of IL-1 signaling cascade, initiated by cytokine binding to ligand-recognition receptor and the following assembly of a co-receptor, triggers the subsequent intracellular signaling pathways. We conducted crystallographic and SAXS studies to understand how the functional flexibility of the IL-1 receptors contributes to specific interactions of cytokine-receptor complexes and how the intrinsic flexibility within IL-1 receptors relevant to molecular recognition [2].

References

[1] C.S. -H, Lin, S. -Y. Chao, J. C. Nix, et al., PLos ONE, 9(2), (2014) e89027.

[2] X. Liu, M. Hammel, Y. He, J. A. Tainer, U.-S. Jeng, L. Zhang, S. Wang and X. Wang, Proc. Natl. Acad. Sci. 110, (2013) 14918.



Name: Shu-Ying Sherry Wang (王淑鶯)

Title and Affiliation: Associate Professor, National Cheng Kung University

E-Mail: sherry523@gmail.com

- Functional flexibility of macromolecules _
- _
- IL-1 signaling complex Zinc-finger DNA binding proteins _

Liquid phase networks of conjugated polymers and carbon allotropes

Jrjeng Ruan, Jui-Hsien Lo and Yu-Chen Deng

¹ Department of Materials Science and Engineering, National Cheng Kung University, Tainan 701, Taiwan

E-mail:jrjeng@mail.ncku.edu.tw

Semiconductive conjugated polymers, including polyfluorenes and polythiophenes, normally are not miscible with insulating polymethylmethacrylate (PMMA) in molten state. Nevertheless, upon the dissolution effect of selected solvents, the liquid phase of PMMA was discovered to coexist with separate liquid phases of conjugated polymers. These polymer liquid phases are able to simultaneously distribute into networks or granular domains upon the variation of mixing ratios. Moreover, as being influenced by favourable π - π interactions with conjugated polymers, functional materials like carbon nanotubes and fullerene derivatives were found to preferably blend into one of polymer liquid phases in these two-phase solutions, as shown in Figure 1. This is a new mechanism for establishing percolation network of functional carbon allotropes within polymeric thin film, providing opportunities of enhancing performances in various aspects, like heat and electronic conduction.

In addition to individual liquid phases of conjugated polymers, the network of phenyl-C61-butyric acid methyl ester (PCBM) liquid phase was found to develop in solutions also upon the addition of conjugated polymers. The involved phase separation can be adjusted by concentration, mixing ratio and the length of alkyl side chian attached on conjugated polymers as well. This prior phase separation is critical for later crystallization of PCBM within precipitated thin film, and networks of PCBM single crystal was found able to develop upon selected thermal treatment (Figure 2). According to these results, it is expected to establish a fundamental mechanism to manipulate the development of complex liquid phases in solutions as a novel way to reach desired structures of optoelectrical thin film.



500 mm HV-80kV Direct Mag: 25088x

Figure 1. Electronic micrograph of preferable dispersion of carbon nanotubes within networks regions of polyfluorene of precipitated thin film



Figure 2. Electronic micrograph of networks of PCBM single crystals, which are covered with overgrowth of board-like crystallites



Name: Jrjeng Ruan (阮至正)

Title and Affiliation: Associate Professor, Department of Materials Science and Engineering, National Cheng Kung University

E-Mail: jrjeng@mail.ncku.edu.tw

- Ordering assembly and crystallization behaviors of organic molecules Polymer blends _
- _
- Phase transition behaviors _

Probing UV-Irradiated and pyrolyzed block copolymer micelles on a solid by grazing incident X-ray Jiun-You Liou, and Ya-Sen Sun*

Department of Chemical and Materials Engineering, National Central University, Taoyuan 32001, Taiwan

**E-mail: yssun@cc.ncu.edu.tw*

We investigated the structural evolution of truncated micelles in ultrathin films of polystyrene-block-poly(2-vinylpyridine), PS-b-P2VP, of monolayer thickness on bare silicon substrates (SiO_x/Si) with UV irradiation in air- (UVIA) and nitrogen-rich (UVIN) environments. The structural evolution of micelles with UV irradiation was monitored with GISAXS measurements in situ while the surface morphology was probed with an atomic force microscope ex situ and the chemical composition with X-ray photoelectron spectra (XPS). This work provides clear evidence for an interpretation of relations between the structural evolution and photochemical reactions in PS-b-P2VP truncated micelles with UVIA and UVIN. Under UVIA treatment, photolysis and cross-linking reactions coexisted within the micelles; photolysis occurred mainly at the top of the micelles whereas cross-linking occurred preferentially at the bottom. The shape and size of UVIA-treated truncated micelles were controlled predominantly by oxidative photolysis reactions, which depended on the concentration gradient of free radicals and oxygen along the micelle height. Because of an interplay between photolysis and photo-crosslinking, the scattering length densities (SLD) of PS and P2VP remained constant. In contrast, UVIN treatments enhanced the contrast in SLD between the PS shell and P2VP core as cross-linking dominated over photolysis in the presence of nitrogen. The enhancement of the SLD contrast was due to the varied degree of cross-linking under UVIN for the PS and P2VP blocks.^[1]

Next, we developed a method to fabricate arrays of nanostructured carbon materials of high quality, via direct pyrolysis of poly(styrene-*b*-2-vinylpyridine) (PS-*b*-P2VP) block copolymer (BCP) as thin films without small organic molecules incorporated as carbon resources. Prior to pyrolysis, the nanodomains were cross-linked with UV radiation under nitrogen (UVIN). As upon pyrolysis thermal energies impart mobility to nanodomains to overcome the constraints imposed by cross-linked chains, the free surface is inevitably covered with the PS block that has a smaller surface energy; unless favorable interactions with the P2VP block exist at the free surface, the outer layer of carbonaceous films is predominantly composed of the pyrolyzed PS block.^[2-3]

References

[1] Jiun-You Liou and Ya-Sen Sun*, Soft Matter, 11, (2015) 7119.

[2] Yen-Hsing Lu, Jiun-You Liou, Chien-Fu Lin, and Ya-Sen Sun*, RSC Advances, 5, (2015) 105760.

[3]Ya-Sen Sun*, Wei-Hua Huang, Jiun-You Liou, Yen-Hsing Lu, Kuo-Chih Shih, Chien-Fu Lin, and Shao-Liang Cheng, RSC Advances, 5, (2015) 105774.



Name: Ya-Sen Sun (孫亞賢)

Title: Associate professor, Department of Chemical and Materials Engineering, National Central University, Taoyuan 32001, Taiwan

E-Mail: yssun@cc.ncu.edu.tw

- Polymer thin films
- crystallization Behavior of Crystallizable Block Copolymers and Semicrystalline Homopolymers
- Self-assembly of soft matters

Dynamic Quaternary Structure of α -Crystallin

Rintaro Inoue¹, Takumi Takata¹, Norihiko Fujii², Kentaro Ishii³, Susumu Uchiyama^{3, 4}, Nobuhiro Sato¹, Yojiro Oba¹, Kathleen Wood⁵, Koichi Kato³, Noriko Fujii¹ and Sugiyama Masaaki¹

¹Research Reactor Institute, Kyoto University.
²Teikyo Univ., Radioisotope Res. Ctr.
³Okazaki Institute for Integrative Bioscience, Okazaki.
⁴Graduate School of Engineering, Osaka University.
⁵Australian Nuclear Science and Technology Organization.

E-mail: rintaro@rri.kyoto-u.ac.jp

Most of proteins possess proper quaternary structures. Such quaternary structures are not necessary fixed to certain configurations, but rather are fluctuating due to internal dynamics. Interestingly, some of the proteins possess unique quaternary structures and the representative examples of such proteins are small heat-shock proteins (sHSPs). A small monomer with molecular mass ranging from 9 to 43 kDa serves as a building component for assembling into larger oligomeric structures. Such oligomeric structures are strongly influenced by even the subtle change of external environment.

The *a*-crystallin, which has the consensus amino acid sequence to sHSPs, is comprised of two subunits: α A-crystallin and α B-crystallin. It normally existed as aggregated structure consisting of 20~40 subunits. The determinations of oligomeric structure of α -crystallin were also tackled with various state-of-the art experimental techniques due to the unavailability of its crystal structure, however no consensus on the oligomeric structure such as average number of subunits, degree of heterogeneity, spatial configuration of each subunit has been obtained. In addition, the experimental proofs for cooperative subunit kinetics between α -crystallins have been reported by fluorescence resonance energy transfer (FRET), isoelectric focusing method and mass spectrometry. Hence, α -crystallin are continuously engaged in cooperative subunit kinetics between α -crystallins and they can exist as "*Dynamic quaternary structure*" mediated by such subunit kinetics. We therefore can only access to their inherent feature through disclosing the mechanism of cooperative subunits kinetics in *a*-crystallin.

One of the most fascinating properties in neutron scattering is its ability for discerning hydrogen (H) and deuterium (D) through the difference in neutron scattering lengths between them. Deuteration assisted small-angle neutron scattering (DA-SANS) must be a promising method for tracking subunit kinetics in α -crystallins. In addition, mass spectrometry is an unique experimental method for taking the snapshot of distribution of aggregation number.

In this presentation, we studied subunit kinetics of homo-aggregate of α B-crystallin through the complementary use of DA-SANS and mass spectrometry.



Name: Rintaro Inoue (井上 倫太郎)

Title and Affiliation: Associate Professor, Research Reactor Institute, Kyoto University

E-Mail: rintaro@rri.kyoto-u.ac.jp

- Dynamics and structure of biomolecule
- Soft matter
- Small angle scattering

The correlation between the mechanics of a lipid membrane and its cellular functions

Yi-Fan Chen¹

¹ Department of Chemical and Materials Engineering, National Central University, Taoyuan, 32001, Taiwan.

E-mail: yifanchen@ncu.edu.tw

The spontaneous curvature, C_0 , and the bending modulus, K_{cp} , are two collective properties of a lipid membrane. These two properties manifest the mechanics of a biomembrane and are intertwined with its biological functions. Contrary to the common perception, biomembranes assume nonlamellar structures in many cellular events, with the tendency of forming a nonlamellar structure quantified by C_0 and with the extent of the ease to deform biomembranes measured by K_{cp} . In this presentation, the physical principles associating the mechanics with the functions of biomembranes and the biological relevance of the two collective properties are revealed through exploring the correlations between C_0 and $[Ca^{2+}]$ ($[Ca^{2+}]$ is an important factor in many cellular events that involve the formation of nonlamellar biomembranes), and through those between C_0/K_{cp} and the membrane fusion (membrane fusion is a collection of cellular events that see two disparate membranes, as well as the volumes enclosed by them, merged). From the C_0 -[Ca²⁺] correlations of different lipid speices, we recognize that the charge density of the lipid headgroup is dominant in dictating the structural preferences of anionic phospholipids, and that displaying differential C_0 sensitivities to $[Ca^{2+}]$ is crucial for anionic phospholipids to fulfil their differential biological roles. Furthermore, the dependence on the two collective properties of the fusion capability indicates that an inter-membrane interaction that has seldom been characterized is in fact important to the fusion efficiency of a lipid membrane, and that the negative C_0 -induced promotion of fusion is enabled via increasing the energetic cost of maintaining the membranes in the planar conformation, with respect to transforming them to the nonlamellar structures of the fusion intermediates.

References

[1] Y. -F. Chen*, K. -Y. Tsang, W. -F. Chang and Z. -A. Fan, Soft Matt., 11, (2015) 4041.



Name: Yi-Fan Chen (陳儀帆)

Title and Affiliation: Assistant professor, Department of Chemical and Materials Engineering, National Central University

E-Mail: yifanchen@ncu.edu.tw

- Biological Physics
- Soft Condensed Matter/Biological Liquid Crystals
- Applications of High Pressure Physics
- Application of Scattering and Crystallography Techniques

Structural insights into molecular assembly in the proteasomal systems

Tadashi Satoh¹, Arunima Sikdar^{1,2,3}, Kazuyoshi Murata⁴, Toshiya Kozai⁵, Kentaro Ishii⁶, Masanori Noda⁷, Hiroki Kawamura¹, Hirokazu Yagi¹, Maho Yagi-Utsumi^{1,3}, Susumu Uchiyama^{6,7}, Takayuki Uchihashi⁵, and Koichi Kato^{1,2,3,6}

¹Faculty and Graduate School of Pharmaceutical Sciences, Nagoya City University
²School of Physical Sciences, SOKENDAI (The Graduate School for Advanced Studies)
³Institute for Molecular Science, National Institutes of Natural Sciences
⁴National Institute for Physiological Science, National Institutes of Natural Sciences
⁵Department of Physics, Kanazawa University
⁶Okazaki Institute for Integrative Bioscience, National Institutes of Natural Sciences
⁷Graduate School of Engineering, Osaka University

E-mail: tadashisatoh@phar.nagoya-cu.ac.jp

The proteasome is a huge proteolytic machine consisting of a number of subunits. For example, the catalytic core particle is composed of seven different homologous α -subunits and seven different homologous β -subunits. Accumulating evidence has revealed that the assembly of the eukaryotic proteasome is not spontaneous self-organization but an ordered process assisted by assembly chaperones that transiently associate with the assembly intermediates. Although several proteasome assembly intermediates have been identified, a blueprint for molecular assembly of this huge machine remains to be clarified. We performed biophysical studies of human proteasome subunits $\alpha 6$ and $\alpha 7$ and revealed that the isolated $\alpha 7$ subunit exclusively exists as homo-tetradecamer in solution. We also proposed a "scrap and build" mechanism whereby its double-ring structure is disassembled upon the addition of $\alpha 6$, resulting in a 1:7 hetero-octameric $\alpha 6-\alpha 7$ complex [1].

In this study, we performed comprehensive biophysical studies including analytical ultracentrifugation, mass spectrometry, X-ray crystallography, electron microscopy, and high-speed atomic force microscopy in the eukaryotic and archaeal proteasomal systems. In the eukaryotic system, we expand our previous investigations on human $\alpha 6-\alpha 7$ subunits to include the five remaining $\alpha 1-\alpha 5$ subunits to gain structural insights into α -ring assembly mechanisms. In contrast to the eukaryotic proteasomes, archaeal proteasome subunits are spontaneously assembled. Nevertheless, recent bioinformatic analysis identified archaeal homologs of proteasome assembly chaperones. We demonstrated that these archaeal homologs adopt quite distinct quaternary structures, i.e., homo-tetramer, homo-pentamer, and hetero-eicosamer, as compared with the hetero-dimeric eukaryotic counterparts. We will present our latest results regarding dynamic processes of proteasomes and interactions of the related proteins.

References

[1] K. Ishii, M. Noda, H. Yagi, R. Thammaporn, S. Seetaha, T. Satoh, K. Kato, and S. Uchiyama, *Sci Rep*, 5, (2015) 18167.



Name: Tadashi Satoh (佐藤 匡史)

Title and Affiliation: Associate professor, Graduate School of Pharmaceutical Sciences, Nagoya City University

E-Mail: tadashisatoh@phar.nagoya-cu.ac.jp

- _
- Structural biology Posttranslational modification _
- _ X-ray crystallography

Current Status and Results on J-PARC/MLF Toshiji Kanaya¹ and <u>Hideki Seto¹</u>

¹ J-PARC Center, High Energy Accelerator Research Organization, 203-1 Shirakata, Tokai 319-1106, Japan

E-mail: hideki.seto@kek.jp

Last year, MLF has started operation from February 22 after the recovery from a small fire incident in the second experimental hall. It stopped again due to a leakage of cooling water from the neutron target vessel on April 30 during the 500 kW proton beam operation. After the improvement of the target vessel, MLF restarted on October 27 at 500 kW for the user program. However, it stopped again due to the cooling water leakage from the neutron target vessel. We are now investigating the cause of the problem to develop a new type target vessel. The user program will restart at low power (~200 kW) in the middle of February 2016 by replacing the neutron target vessel to a reserved one.

In MLF, 21 neutron instruments have been funded. Within these instruments, 19 are in operation for the user program and 2 instruments are under commissioning or construction. Now the experimental hall is almost full with instruments, leaving only 2 ports are available for instruments in future.

World-class scientific outputs have been already created in various scientific fields, ranging from basic science to industrial application. Since J-PARC is internationally open for users, we have got experimental proposals from abroad more than 10% of the whole proposals. More than 20% of proposals have come from industrial users and a half of them are proprietary use. This fact has revealed a new horizon has come in the neutron scattering science in the 21st century.



Name: Hideki Seto (瀬戸 秀紀)

Title and Affiliation: Professor, Institute of Materials Structure Science, High Energy Accelerator Research Organization

E-Mail: hideki.seto@kek.jp

- Softmatter Physics -
- _
- Small Angle Scattering Quasi-Elastic Neutron Scattering _
- Tribology _

Nanostructured Networks in Chiral Block Copolymers Rong-Ming Ho

Department of Chemical Engineering, National Tsing Hua University, Taiwan

E-mail: rmho@mx.nthu.edu.tw

The designs of nanostructured materials and corresponding morphologies have attracted intensive attention because of their effectiveness in tuning electronic, optical, magnetic, and catalytic properties as well as mechanical properties. Nanostructured networks are perhaps the most fascinating morphology due to their high porosities and large specific surface areas as well as superior mechanical properties with self-supporting character. Although many technologies have been explored to fabricate nanostructured networks, self-assembly is one of the most important approaches to fabricate nanostructured materials with precisely controlled structures and morphologies from constituted components. Here, we aim to exploit the self-assembly of degradable block copolymers with chiral segments as a powerful tool to fabricate well-defined nanostructured networks. Subsequently, the fabrication of well-ordered nanoporous polymers with continuous nanochannels from the self-assembly of degradable block copolymers (BCPs), such as gyroid-forming network morphologies, can be obtained by degeneration of constituted segment(s) and used as templates for syntheses of various materials with different entities.

References

R.-M. Ho, et al., *Macromolecules*, 47, (2014) 7993. Front Cover Story
R.-M. Ho, et al., *Chem. Soc. Rev.*, 44, (2015) 1974.



Name: Rong-Ming Ho (何榮銘)

Title and Affiliation: Distinguished Professor, Department of Chemical Engineering, National Tsing Hua University, Taiwan

E-Mail: rmho@mx.nthu.edu.tw

- Self-assembly of Macromolecules and Supramolecules
- Hybridization of organic and inorganic Materials
- Nanopatterning Technologies from Bottom-up Methods
- Block Copolymer Physics
- Crystallization Behavior of Polymers

Hierarchical Structure of Polymer/Nanoparticle Hybrid Yu-Chiao Lin¹, Chun-Yu Chen², Hsin-Lung Chen^{1*} and Takeji Hashimoto^{1,3*},

¹Deptartment of Chemical Engineering and Frontier Research Center on Fundamental and Applied Sciences of Matters, National Tsing Hua University, Hsinchu 30013, Taiwan

²National Synchrotron Radiation Research Center, Hsinchu 300, Taiwan

³Quantum Beam Science Center, Japan Atomic Energy Agency, Tokai-Mura, Naka-gun, Ibaraki Pref. 319-1195, and Kyoto University, Kyoto 606-6501, Japan (Professor Emeritus).

E-mail: hlchen@che.nthu.edu.tw

Using small angle X-tray scattering (SAXS), we elucidated the spatial organization of palladium (Pd) nanoparticles (NPs) in the polymer matrix of poly(2-vinylpyridine) (P2VP) and the nature of inter-nanoparticle interactions, where the NPs were synthesized in the presence of P2VP by the reduction of palladium acetylacetonate (Pd(acac)₂). The experimental SAXS profiles were analysed on the basis of a hierarchical structure model considering the following two types of interparticle potential: (i) hard-core repulsion only (i.e., the hard-sphere interaction) and (ii) hard-core repulsion together with an attractive potential well (i.e., the sticky hard-sphere interaction). The corresponding theoretical scattering functions, which were used for analysing the experimental SAXS profiles, were obtained within the context of the Percus-Yevick closure and the Ornstein-Zernike equation in the fundamental liquid theory. The analyses revealed that existence of the attractive potential well is indispensable to account for the experimental SAXS profiles. Moreover, the morphology of the hybrids was found to be characterized by a hierarchical structure with three levels, where about six primary NPs with the diameter of ca. 1.8 nm (level one) formed local clusters (level two), and these clusters aggregated to build up a large-scale mass-fractal structure (level three) with the fractal dimension of ca. 2.3. The scattering function developed here is of general use for quantitatively characterizing the morphological structures of polymer/NP hybrids and in particular for exploring the interaction potential of the NPs on the basis of the fundamental liquid theory.



Name: Hsin-Lung Chen (陳信龍)

Title and Affiliation: Professor, Department of Chemical Engineering, National Tsing Hua University

E-Mail: hlchen@che.nthu.edu.tw

- Self-organization of DNA complexes for gene delivery and biomimetics
- Phase behavior of block copolymers
- Molecular aggregation of conjugated polymers
- Hierarchical structure of polymer nanohybrids

KUR REPORT OF KYOTO UNIVERSITY RESEARCH REACTOR INSTITUTE

発行所	京都大学原子炉実験所
発行日	平成 28 年 3 月
住所	大阪府泉南郡熊取町朝代西2丁目
	TEL (072) 451-2300